

Technical Data Sheet

TDS Number :- 48

Q.C.Spec:	Internal
Product Code:	50 GSM
Product Type:	Spunmelt
Treatment:	Hydrophobic

Properties	Units	Test Method	LSL	USL
Appearance/ Visual inspection	Fabric is free from Dust, Smell, insect, Drops, Drips, Holes, Broken Filaments & Other Contamination.			
Weight	g/m ²	NWSP 130.1.R0(20)	48	52
Tensile Strength MD	N/5 cm	NWSP 110.4.R1(24)	100	N/A
Tensile Strength CD	N/5 cm	NWSP 110.4.R1(24)	50	N/A
Tensile Elongation MD	%	NWSP 110.4.R1(24)	40.00	120
Tensile Elongation CD	%	NWSP 110.4.R1(24)	40.00	120
Water resistance@100cm ²	mbar	NWSP 080.6.R0(23)	520	N/A
Air Permeability@38 cm ²	l/m ² /s@ 125Pa	NWSP 070.1.R0(20)	180	280
Slit Roll Specification & Packaging Standard			Capacity	Tolerance
Width	MM	By Std. Measuring tape	60-4200	≤500±3 & 500-4200±5
Roll Diameter	MM	By Std. Measuring tape	Max.1200	±20
Length	Mtr	Encoder/Length Meter	As per requirement	±50
Paper Core	Inch	3 & 6		
Type of Splice	Normal Black Tape			
Details Of Splice	No. of 1 Splice allowed per roll and Splice Material Only 10% dispatch per Container.			
Corrugated Sheet	One Side/Both Side			
Type Of Packing	With Pallet/Without Pallet			
Wrapping	Strong Plastic (Stretch Film)			

Note: -Typical Properties are based on Ktex Nonwovens specification and can be achieved according to specific Customer requirements.

Priti Verma

Niraj Bhatti

Prepared By

Approved By



MANUFACTURER:-
Ktex Nonwovens Pvt. Ltd.
Survey No 241, Sanosara,
Opp. Khamta Bus Stop, Jamnagar Highway,
Village - Khamta, Tal - Dhrol,
Jamnagar, 360110, Gujarat, India.
Tel #: +91-9727055055